


# 4379M-74

## Differential Double-Coated Polyester Film Tape



Release Liner: 74# Polycoated Kraft  
 Liner Side Adhesive: Rubber (I924)  
 Backing/Carrier: 0.5 mil PET Film  
 Air Side Adhesive: Acrylic (I639)

### Applications

- Bonding to a variety of ether, ester, and low perm urethane foams
- LSE bonding including mica-filled polypropylene

### Features

- Acrylic Adhesive
- Polyester Film Carrier
- Rubber Adhesive
- 74# Polycoated Kraft Liner

### Benefits

- Excellent heat resistance
- Low fogging (tested at 24 hrs, 200 °F)
- Biostatic additive resists microbial growth
- Support for aid in processing and application
- Conformable
- Offers exceptionally high tack and high peel
- Designed for bonding to various foams, as well as rough and porous surfaces
- Conformable and good dimensional stability
- Moisture stable

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
Overall Thickness (w/liner)	9.1 mils	0.231 mm	PSTC 133
Air-Side Adhesive Thickness	1.3 mils	0.033 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Liner Side Adhesive Thickness	1.8 mils	0.046 mm	PSTC 133
Liner Thickness	5.5 mils	0.140 mm	PSTC 133
Adhesion to Steel (Air Side)	56 oz/in	6.13 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Liner Side)	155 oz/in	16.96 N/cm	PSTC 101 Mod - 1 mil PET
Shear Strength (Room Temp)	7 days		PSTC 107 Mod
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 180 °F	-1 to 82 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F  
 Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at VYBOND GROUP, INC. (Vybond Group, Inc. 2320 Bowling Green Road, Franklin, KY 42134) by qualified technical personnel. To VYBOND'S knowledge, it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state, and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which VYBOND assumes any legal responsibility.