


## Economy Self-Wound Flashing Tape



- Backing:** Polypropylene (printed and unprinted)
- Adhesive:** Acrylic
- Colors:** White, Black, Clear
- Specifications:** AMAA 711-22 for Self-Adhering Flashing Used for Installation of Exterior Wall Fenestration Products
- Standard Sizes:** 2in x 75ft, 4in x 75ft, 6 x 75ft, 9 x 75ft, 12in x 75ft

### Applications

- Structural insulated sheathing (SISs) and Structural Insulated Panels (SIPs) seams
- Window & Door Installations
- Corner Board Abutments
- Sealing other detail areas against water and air penetration

### Features

- Polypropylene Backing
- Acrylic Adhesive
- Self-Wound Construction

### Benefits

- Excellent conformability for bonding around curves and corners
- Durable and strong
- Excellent cold-temperature adhesion
- Excellent adhesion to variety of substrates
- Provides permanent weather-tight seal on most clean, dry building surfaces
- Compatible with sealants and caulking
- Self-healing after puncture
- Less jobsite waste
- Faster installations

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness</b>	9.5 mils	0.241 mm	ASTM D-1000
<b>Adhesion to OSB</b>	67 oz/in	7.35 N/cm	ASTM D3330 Method F
<b>Adhesion to Aluminum</b>	144 oz/in	15.76 N/cm	ASTM D3330 Method F
<b>Adhesion to Vinyl</b>	144 oz/in	15.76 N/cm	ASTM D3330 Method F
<b>Adhesion to Plywood</b>	133 oz/in	14.54 N/cm	ASTM D3330 Method F
<b>Adhesion to Backing</b>	38 oz/in	4.20 N/cm	ASTM D3330 Method F
<b>Tensile Strength</b>	25 lb/in	44.50 N/cm	ASTM D3759 Procedure A
<b>Elongation</b>	820%		ASTM D3759 Procedure A
<b>Installation Temperature</b>	20 to 180 °F	-7 to 82 °C	
<b>Operating Temperature</b>	-30 to 200 °F	-34 to 93 °C	
<b>UV Exposure</b>	1 year (Black and White), 9 months (Clear)		

Recommended Storage Conditions: 60-80 °F at 40-60% RH

Standard Shelf Life (at 25 °C): 36 months from date of manufacture.

The information presented herein was prepared at VYBOND GROUP, INC. (Vybond Group, Inc. 2320 Bowling Green Road, Franklin, KY 42134) by qualified technical personnel. To VYBOND'S knowledge, it is true and accurate. However, the information and

The information presented herein was prepared at VYBOND GROUP, INC. (Vybond Group, Inc. 2320 Bowling Green Road, Franklin, KY 42134) by qualified technical personnel. To VYBOND'S knowledge, it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state, and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which VYBOND assumes any legal responsibility.