


D9200

FR Waterseal Tape & Corrosion Inhibitor



Backing: Exterior-Grade Aliphatic Polyurethane

Adhesive: FR Acrylic

Liner: Blue HDPE

Colors: Transparent

Specifications: FAR 25.853(a); Fokker Fk05-193

Size Options: Incremental sizes 1/4" - 48" x 108Ft

Applications

- Floor joint sealing on aircraft decking in all wet areas including: entryways, galleys, lavatories, and more
- Anti-slip tape for aircraft overhead bins
- Moisture barrier applications
- Reinforcement and moisture barrier for aircraft insulation fastener openings
- Surface protection for high wear areas

Features

Benefits

- | | |
|---|---|
| <ul style="list-style-type: none"> • Polyurethane Film Backing | <ul style="list-style-type: none"> • Protects and holds under heavy usage • Tough and elastic • Excellent lay flat and dimensional stability • Transparent to allow for visual inspection |
| <ul style="list-style-type: none"> • FR Acrylic Adhesive | <ul style="list-style-type: none"> • Strong permanent bond • Meets FAA flammability standards • Compatible with sealants • Repositionable |
| <ul style="list-style-type: none"> • Blue HDPE Release Liner | <ul style="list-style-type: none"> • Smooth clean release - easy to use • Die cuttable |

Typical Test Values

	Standard UOM		Metric UOM		Test Method
Total Thickness	14.0	mils	0.356	mm	PSTC-133
Substrate Thickness	12.0	mils	0.305	mm	PSTC-133
Adhesion to Steel	80	oz/in	8.75	N/cm	ASTM D-3330
Tensile Strength	80	lb/in	140.10	N/cm	ASTM D-3759
Puncture Resistance	40	lbs	18.14	kg	ASTM D-1000
Elongation	500%				
Weight	12.60	oz/yd ²	427.21	g/m ²	
Application Temperature	50 °F to 120 °F		10 °C to 49 °C		
Operating Temperature	-40 °F to 275 °F		-40 °C to 135 °C		

Recommended Storage Conditions: 40-60% Humidity, 60 - 80 °F

Standard Shelf Life (at 25 °C): 24 months from date of manufacture

The information presented herein was prepared at VYBOND GROUP, INC. (Vybond Group, Inc. 2320 Bowling Green Road, Franklin, KY 42134) by qualified technical personnel. To VYBOND'S knowledge, it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state, and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which VYBOND assumes any legal responsibility.